

Einsatzwerte NC-Anbohrer VHM 120° unbeschichtet (Art.-Nr. 1010906 103-120)



| Materialgruppen für Schnittwerte | Festigkeit [N/mm ²] | Bezeichnung nach DIN | Vc [m/min] | f [mm/U] bei Durchmesser | | | | | |
|-------------------------------------|--|-------------------------|-----------------------|--------------------------|-----------|-----------|-----------|-----------|-----------|
| | | | | 0-3 | 3-6 | 6-10 | 10-16 | 16-20 | |
| 1. Stähle | | | | | | | | | |
| 1.1 | Automatenstahl | < 900 | 9 S 20 | 60-90 | 0.03-0.05 | 0.05-0.13 | 0.13-0.14 | 0.14-0.15 | 0.15-0.2 |
| 1.2 | Baustahl | <500 | ST 37-2 | 60-85 | 0.03-0.05 | 0.05-0.13 | 0.13-0.14 | 0.14-0.15 | 0.15-0.2 |
| 1.3 | Baustahl | > 500 | ST 60-2 | 60-75 | 0.03-0.05 | 0.05-0.13 | 0.13-0.14 | 0.14-0.15 | 0.15-0.18 |
| 1.4 | Vergütungsstahl | <1000 | 42 CrMo 4 | 40-75 | 0.03-0.05 | 0.05-0.13 | 0.13-0.14 | 0.14-0.15 | 0.15-0.18 |
| 1.5 | Stahlguss | <1000 | GS-45 | 40-75 | 0.03-0.05 | 0.05-0.11 | 0.11-0.12 | 0.12-0.13 | 0.13-0.15 |
| 1.6 | Einsatzstahl | <1200 | 16 MnCr 5 | 50-70 | 0.03-0.05 | 0.05-0.11 | 0.11-0.12 | 0.12-0.13 | 0.13-0.15 |
| 1.7 | Edelstahl ferritisch/ martensitisch | <1100 | X 10 Cr 13 | 20-30 | 0.03-0.05 | 0.05-0.11 | 0.11-0.12 | 0.12-0.13 | 0.13-0.15 |
| 1.8 | Vergütungsstahl | >1000 | 43 CrMo 4 | 30-50 | 0.03-0.05 | 0.05-0.11 | 0.11-0.12 | 0.12-0.13 | 0.13-0.15 |
| 1.9 | Nitrierstahl | <1300 | 31 CrMoV 9 | 30-50 | 0.03-0.05 | 0.05-0.11 | 0.11-0.12 | 0.12-0.13 | 0.13-0.15 |
| 1.10 | Werkzeugstahl | <1300 | X 38 CrMoV 5 1 | 30-50 | 0.03-0.05 | 0.05-0.11 | 0.11-0.12 | 0.12-0.13 | 0.13-0.15 |
| 2. Rostfreie Stähle | | | | | | | | | |
| 2.1 | Edelstahl, austenitisch | <1100 | G-X 2 CrNiMo 18 15 | 15-35 | 0.03-0.05 | 0.05-0.11 | 0.11-0.12 | 0.12-0.13 | 0.13-0.14 |
| 3. NE-Metalle | | | | | | | | | |
| 3.1 | Aluminium, langspanend | <500 | Al99.9 | 180-260 | 0.05-0.14 | 0.14-0.16 | 0.16-0.18 | 0.18-0.22 | 0.22 |
| 3.2 | Aluminium, kurzspanend | <500 | G-AlSi12 | 150-210 | 0.03-0.05 | 0.05-0.14 | 0.14-0.16 | 0.16-0.18 | 0.18-0.22 |
| 3.3 | Kupferleg. Bronze langspanend | <1200 | CuSn4 | 50-90 | 0.03-0.05 | 0.05-0.13 | 0.13-0.14 | 0.14-0.15 | 0.15-0.2 |
| 3.4 | Kupferleg. Bronze kurzspanend | <850 | CuNi12Zn24 | 55-100 | 0.03-0.05 | 0.05-0.13 | 0.13-0.14 | 0.14-0.15 | 0.15-0.2 |
| 3.5 | Kupferleg. Messing langspanend | <600 | Cu Zn 20 | 100-150 | 0.03-0.05 | 0.05-0.05 | 0.05-0.14 | 0.14-0.16 | 0.16-0.18 |
| 3.6 | Kupferleg. Messing kurzspanend | <600 | Cu Zn 39 Pb 3 | 120-170 | 0.03-0.05 | 0.05-0.13 | 0.13-0.14 | 0.14-0.15 | 0.15-0.2 |
| 3.7 | Thermoplastic | <100 | PVC, Acrylglas | 40-60 | 0.03-0.05 | 0.05-0.13 | 0.13-0.14 | 0.14-0.15 | 0.15-0.2 |
| 3.8 | Duroplast | <150 | Bakelit, Melamin | 40-50 | 0.03-0.05 | 0.05-0.13 | 0.13-0.14 | 0.14-0.15 | 0.15-0.2 |
| 3.9 | Faserverstärkte Kunststoffe | <1500 | CFK, GFK | | | | | | |
| 3.10 | Graphite | <60 | C8000 | | | | | | |
| 3.11 | Verbundwerkstoffe | | | | | | | | |
| 4. Guss | | | | | | | | | |
| 4.1 | Grauguss | <260 HB | GG10 | 60-90 | 0.03-0.05 | 0.05-0.12 | 0.12-0.13 | 0.13-0.15 | 0.15-0.17 |
| 4.2 | Sphäroguss | <310 HB | GGG 40 | 60-90 | 0.03-0.05 | 0.05-0.12 | 0.12-0.13 | 0.13-0.15 | 0.15-0.17 |
| 4.3 | Gusseisen mit Kugelgraphit | <280 HB | GTW-55 | 60-90 | 0.03-0.05 | 0.05-0.12 | 0.12-0.13 | 0.13-0.15 | 0.15-0.17 |
| 5. Sonderlegierungen | | | | | | | | | |
| 5.1 | Titanlegierung | <1200 | TiAl5Sn2,5 | 15-40 | 0.01-0.03 | 0.03-0.05 | 0.05-0.06 | 0.06-0.07 | 0.07-0.08 |
| 5.2 | Nickelbasislegierung | <1400 | NiCr21Mo | 15-20 | 0.01-0.03 | 0.03-0.05 | 0.05-0.06 | 0.06-0.07 | 0.07-0.08 |
| 5.3 | Superlegierungen | <1400 | X45CrSi 9 3 | 15-20 | 0.01-0.03 | 0.03-0.05 | 0.05-0.06 | 0.06-0.07 | 0.07-0.08 |
| 6. Harte Werkstoffe | | | | | | | | | |
| 6.1 | Stahl gehärtet -55HRC | -55HRC | x40CrMoV5-1 | 10-18 | 0.01-0.03 | 0.03-0.05 | 0.05-0.06 | 0.06-0.07 | 0.07-0.08 |
| 6.2 | Stahl gehärtet -65HRC | <65HRC | 90MnCrV8 | | | | | | |

