

Einsatzwerte

Mehrbereichsgewindefräser mit Halseinstich VHM 15° Zylinderschaft HA
(Art.-Nr. 1003141 677-679)



Materialgruppen für Schnittwerte	Festigkeit [N/mm ²]	Bezeichnung nach DIN	Vc [m/min]	f [mm/U] bei Durchmesser			
				1-8	8-10	10-20	
1. Stähle							
1.1	Automatenstahl	< 900	9 S 20	100-200	0.03-0.06	0.06-0.1	0.1-0.2
1.2	Baustahl	<500	ST 37-2	100-200	0.03-0.06	0.06-0.1	0.1-0.2
1.3	Baustahl	> 500	ST 60-2	100-180	0.03-0.06	0.06-0.1	0.1-0.2
1.4	Vergütungsstahl	<1000	42 CrMo 4	110-150	0.02-0.05	0.05-0.08	0.08-0.18
1.5	Stahlguss	<1000	GS-45	110-150	0.02-0.05	0.05-0.08	0.08-0.18
1.6	Einsatzstahl	<1200	16 MnCr 5	90-140	0.02-0.05	0.05-0.08	0.08-0.16
1.7	Edelstahl ferritisch/ martensitisch	<1100	X 10 Cr 13	80-130	0.01-0.04	0.04-0.07	0.07-0.14
1.8	Vergütungsstahl	>1000	43 CrMo 4	60-120	0.01-0.04	0.04-0.07	0.07-0.14
1.9	Nitrierstahl	<1300	31 CrMoV 9	60-90	0.01-0.04	0.04-0.07	0.07-0.12
1.10	Werkzeugstahl	<1300	X 38 CrMoV 5 1	60-90	0.01-0.04	0.04-0.07	0.07-0.12
2. Rostfreie Stähle							
2.1	Edelstahl, austenitisch	<1100	G-X 2 CrNiMo 18 15	100-120	0.01-0.04	0.04-0.07	0.07-0.12
3. NE-Metalle							
3.1	Aluminium, langspanend	<500	Al99.9	160-250	0.04-0.08	0.08-0.12	0.12-0.22
3.2	Aluminium, kurzspanend	<500	G-AlSi12	150-240	0.04-0.08	0.08-0.12	0.12-0.22
3.3	Kupferleg. Bronze langspanend	<1200	CuSn4	100-200	0.03-0.06	0.06-0.1	0.1-0.2
3.4	Kupferleg. Bronze kurzspanend	<850	CuNi12Zn24	100-200	0.03-0.06	0.06-0.1	0.1-0.2
3.5	Kupferleg. Messing langspanend	<600	Cu Zn 20	160-240	0.04-0.08	0.08-0.12	0.12-0.22
3.6	Kupferleg. Messing kurzspanend	<600	Cu Zn 39 Pb 3	160-240	0.04-0.08	0.08-0.12	0.12-0.22
3.7	Thermoplastic	<100	PVC, Acrylglas	100-350	0.04-0.08	0.08-0.12	0.12-0.22
3.8	Duroplast	<150	Bakelit, Melamin	100-250	0.04-0.08	0.08-0.12	0.12-0.22
3.9	Faserverstärkte Kunststoffe	<1500	CFK, GFK				
3.10	Graphite	<60	C8000				
3.11	Verbundwerkstoffe						
4. Guss							
4.1	Grauguss	<260 HB	GG10	70-130	0.03-0.06	0.06-0.1	0.1-0.2
4.2	Sphäroguss	<310 HB	GGG 40	70-110	0.03-0.06	0.06-0.1	0.1-0.2
4.3	Gusseisen mit Kugelgraphit	<280 HB	GTW-55	70-110	0.03-0.06	0.06-0.1	0.1-0.2
5. Sonderlegierungen							
5.1	Titanlegierung	<1200	TiAl5Sn2,5	20-60	0.02-0.04	0.04-0.05	0.05-0.06
5.2	Nickelbasislegierung	<1400	NiCr21Mo	20-60	0.02-0.04	0.04-0.05	0.05-0.06
5.3	Superlegierungen	<1400	X45CrSi 9 3	20-60	0.02-0.04	0.04-0.05	0.05-0.06

