

Einsatzwerte VHM Radiusfräser (Art.-Nr. 1016407 101-109)



ae x D	ap x D	Faktor
0.1	2	1
0.3	1.5	0.7
0.5	1	0.8
0.8	0.75	0.5
1	0.5	0.4

Materialgruppen für Schnittwerte	Festigkeit [N/mm ²]	Bezeichnung nach DIN	Vc [m/min]	fz [mm/Z] bei Durchmesser					
				4-6	6-8	8-10	10-12	12-16	16-20
1. Stähle									
1.1	< 900	9 S 20	130-150	0.03-0.04	0.04-0.044	0.044-0.058	0.058-0.063	0.063-0.082	0.082-0.11
1.2	<500	ST 37-2	140-160	0.03-0.04	0.04-0.044	0.044-0.058	0.058-0.063	0.063-0.082	0.082-0.11
1.3	> 500	ST 60-2	140-160	0.03-0.04	0.04-0.044	0.044-0.058	0.058-0.063	0.063-0.082	0.082-0.11
1.4	<1000	42 CrMo 4	130-150	0.03-0.04	0.04-0.044	0.044-0.058	0.058-0.063	0.063-0.082	0.082-0.11
1.5	<1000	GS-45	130-150	0.03-0.04	0.04-0.044	0.044-0.058	0.058-0.063	0.063-0.082	0.082-0.11
1.6	<1200	16 MnCr 5							
1.7	<1100	X 10 Cr 13							
1.8	>1000	43 CrMo 4							
1.9	<1300	31 CrMoV 9							
1.10	<1300	X 38 CrMoV 5 1							
2. Rostfreie Stähle									
2.1	<1100	G-X 2 CrNiMo 18 15	65-85	0.025-0.035	0.035-0.038	0.038-0.05	0.05-0.055	0.055-0.073	0.073-0.1
5. Sonderlegierungen									
5.1	<1200	TiAl5Sn2,5	60-80	0.025-0.043	0.043-0.048	0.048-0.064	0.064-0.068	0.068-0.095	0.095-0.12
5.2	<1400	NiCr21Mo	60-80	0.022-0.03	0.03-0.036	0.036-0.048	0.048-0.051	0.051-0.07	0.07-0.09
5.3	<1400	X45CrSi 9 3	60-80	0.025-0.043	0.043-0.048	0.048-0.064	0.064-0.068	0.068-0.095	0.095-0.12

